

SILICONE COMPOUND DM<sup>TM</sup> MOISTURE PROOFING SEALANT & LUBRICANT 广州孚润 400-992-6811

## DESCRIPTION

JET-LUBE'S SILICONE COMPOUND DM<sup>™</sup> 2 & 3 are premium silicone compounds for use in a wide variety of applications. Its low volatility, non-melting thickener and high dielectric strength make it the compound of choice for moisture proofing ignition systems, spark plug connections, electrical assemblies, cable and battery terminals and other similar applications.

**SILICONE COMPOUND DM** provides excellent lubrication and sealing properties for plug and gate valves, stuffing boxes, o-rings, and vacuum and pressure systems. The low volatility and inert properties allow it to be used on a wide range of elastomers and plastics and is ideally suited for subzero processing facilities and spiral freezer applications. It is not recommended for use on surfaces to be painted.

- NSF H-1 Registered #132225 (DM-3), #132225 (DM-2)
- · Excellent for high temperature bearings, conveyor
- systems, and low-temp refrigeration systems.
- Water resistant
- Nontoxic/Safe
- · Wide temperature range
- Chemical resistant
- Translucent paste
- Highly resistant to oxidation and shear breakdown
- Suitable for valve lubrication
- Dielectric strength: > 500 volts/mil typical
- Conforms to: SAE AS8660 (DM-3)
  - MIL C-21567A (DM-2)
- NATO Code #S-736

NOTE: Standard Grade is NLGI 3

## **PRODUCT CHARACTERISTICS**

Thickener Color/Appearance Specific Gravity Penetration Oil Separation, Wt. % (24 hrs. @ 100°C) Temperature Range

Dielectric Strength (ASTM D149, 1.27mm gap) Dielectric Constant @ 100 Hz Dissipation Factor @ 100 Hz (ASTM D150) Volume Resistivity @ 23 °C (ASTM D257) Inorganic White translucent gel 1.05 220 - 250 <1.0%

-50°F (-46°C) to 400°F (204°C) 15.54 kV/mil

2.8 0.0000933

1.59 x 1017 ohm-cm

## For package types and part numbers contact sales@jetlube.com

## LIMITED WARRANTY

For warranty information please visit http://www.jetlube.com/pdf/Jet-Lube Warranty.pdf

You can also email us at <u>sales@jetlube.com</u> or write to the Sales Department at the address below.