

MOLYLUBE® EXTREME PRESSURE GREASE AC

Molylube Extreme Pressure Grease AC, commonly known as Molylube 126 EP Grease, is a mineral oil based, Extreme Pressure aluminum complex grease. Because it is an aluminum complex grease, **Molylube Extreme Pressure Grease AC** exhibits all of the beneficial characteristic of that thickener, including resistance to water washout, excellent pumpability, and mechanical and thermal stability. **Molylube Extreme Pressure Grease AC**'s low oil separation and good pumpability make it ideal for use in centralized lubrication systems. It's recommended for general greasing of mining machinery.

Applications

- Dragline and shovel main machinery bearings, slewing bearings, crawler pins and bushings, bucket pins
- Process machinery and general plant lubrication
- Manual or automatic lubrication of rolling stock chassis, articulated joints and run-of-themine vehicles

Features and Benefits

| ٠ | Extreme Pressure and anti-wear properties | Maximizes component useful life helping to reduce replacement part costs and lost production time. | | | |
|---|--|--|--|--|--|
| ٠ | Water resistant | Maximizes bearing retention in wet environments. | | | |
| • | Molylube lubricating solids | An effective level of lubricating solids for improved load carrying protection and friction reduction. Extends component life. | | | |
| • | Exceptional mechanical and thermal stability | Maximizes bearing retention in high shear and high temperature environments. | | | |

General Description

Molylube Extreme Pressure Grease AC is a multi-purpose, Extreme Pressure, water resistant lubricant manufactured with paraffinic base oils, an aluminum complex thickener and rust and oxidation inhibitors. **Molylube Extreme Pressure Grease AC** provides outstanding film strength, adhesive properties and superior wear protection in heavily loaded and shock-load conditions. This product provides excellent lubrication over a wide range of operating conditions.

Product No. 301200, 301201, 301696

Page 1 of 2

1/2/2018

With continual research and development, Calumet reserves the right to change the information contained herein. The Company is not responsible for misuse or misapplication of its products.

MOLYLUBE® EXTREME PRESSURE GREASE AC

TYPICAL PROPERTIES

| Product No. | <u>301200</u> | <u>301201</u> | <u>301696</u> |
|--|---------------|---------------|---------------|
| <u>Old Product No.</u> | <u>23200</u> | <u>23220</u> | <u>23240</u> |
| NLGI Grade Penetration, worked (60 strokes), ASTM D217 | AC 0 | AC 1 | AC 2 |
| mm/10 | 370 | 325 | 280 |
| Viscosity (Base Fluid), ASTM D445 @ 40°C, cSt | 150 | 220 | 180 |
| @ 100°C, cSt | 14.87 | 19.3 | 16.2 |
| Viscosity (Base Fluid), ASTM D2161 @ 100°F, SUS | 786 | 1160 | 950 |
| @ 210°F, SUS | 79.1 | 98.1 | 84.7 |
| Dropping Point, ASTM D2265 °C | 237 | 248 | 254 |
| (°F) | (458) | (478) | (489) |
| Pumpability, Lincoln Ventmeter, from 1800 psi @ Room Temperature, ~25°C (~77°F) psi | 0 | 250 | 300 |
| @ -1°C (30°F), psi | 200 | 230 525 | 500 600 |
| @ -18°C (0°F), psi | 800 | 1125 | 1300 |
| Water Washout, ASTM D1264 | | | |
| @ 79°C (175°F), loss, weight % | 4.8 | 3.5 | 1.8 |
| 4-Ball EP Test, ASTM D2596 | (20) | (20) | (20) |
| Weld Load, kg Load Wear Index, kg | 620 99 | 620 99 | 620 99 |
| Timken EP Test, ASTM D2509 | | | |
| OK Load, kg (lb) | 29.5 (65) | 29.5 (65) | 29.5 (65) |
| 4-Ball Wear Test, 40 kg, 1 hr, 75°C Scar Diameter, mm | 0.65 | 0.68 | 0.67 |
| Rust Protection, ASTM D1743, rating | Pass | Pass | Pass |
| Color | Black | Black | Black |

Page 2 of 2

1/2/2018

With continual research and development, Calumet reserves the right to change the information contained herein. The Company is not responsible for misuse or misapplication of its products.

Calumet Branded Products, LLC • P.O. Box 526 • Farmingdale, NJ 07727 USA TEL +1 732-938-2421 • FAX +1 732-938-4232 • www.belray.com