

FLUOROCARBON GEL 868

广州孚润 400-992-6811

Rust Inhibited

A PTFE thickened, medium viscosity, synthetic hydrocarbon grease intended for automotive and industrial controls which require a light tack and minimal change in damping characteristics with temperature.

	Lubricant Properties		Typical value	Test Method
Recommended Service Range (°C)		-40 to 125		
Thickener			PTFE	
Base oil	Туре		Polyalphaolefin	
	Kinematic viscosity	-40°C	> 1000000 cSt	ASTM D-445
		40°C	5548 cSt	
		100°C	525 cSt	
	Viscosity Index		280	ASTM D-2270
	Flash point	C°	> 200	ASTM D-92
	Pouring point	C°	-30	ASTM D-97
	Typical Properties of	the	Typical value	Test Method
	Grease			
Color, Appearance			White	
Penetration	NLGI Grade		2	ASTM D-217
(1/10 mm)	Worked	60X	277	ASTM D-217
	Unworked		293	ASTM D-217
Density		25°C	1.16 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	100°C	0	FTM 791, Method 321.2
Evaporation	24 hour(s)	100°C	0.2	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1510)

Distributed by Newgate Simms Limited

Broughton Mills Road, Bretton, Chester, CH4 0BY, United Kingdom +44(0)1244 660771 www.newgatesimms.com info@newgatesimms.com

Nye Lubricants, Inc. 12 Howland Road, Fairhaven, MA 02719 USA Ph: 1.508.996.6721 Fx: 1.508.997.5285 nyelubricants.com