

FLUOROCARBON GEL 885

广州孚润 400-992-6811

A soft, PTFE thickened, heavy viscosity, dimethyl silicone grease intended for efficient lubrication of automotive cables and other low friction applications.

GM: 9986661 & NSF-61 Potable Water Lubricant Registered

	Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)			-40 to 200	
Thickener			PTFE	
Base Oil	Туре		Dimethyl Silicone	
	Kinematic Viscosity	100°C	175 cSt	ASTM D-445
		40°C	410 cSt	
	Viscosity Index		458	ASTM D-2270
	Flash Point	°C	254	ASTM D-92
	Pour Point	°C	-62	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			White,Smooth	
Penetration	Unworked		339	ASTM D-217
(1/10 mm)	Worked	60X	335	
Density		25°C	1.2 g/cm ³	NYE CTM
Oil Separation	24 hour(s)	150°C	9.63	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.05 %	ASTM D-972
		150°C	3.06 %	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1603)