

## NYE NYOGEL<sup>®</sup> 753G

A stiff, carbon thickened, light viscosity, polyolester grease intended for wide temperature applications where a degree of electrical conductivity in the grease is required.

## 广州孚润 400-992-6811

## The SmartGrease Company

Lubricant Properties			Typical Value	Test Method
Recommended Service Range (°C)			- 40 to 150	
Thickener			Carbon	
	Туре		Polyolester	
Base Oil	Kinematic Viscosity cSt (mm²/s)	100°C	9.0	ASTM D-445
		40°C	57.0	
		-40°C	37,000	
	Viscosity Index		142	ASTM D-2270
	Flash Point (°C)		285	ASTM D-92
	Pour Point (°C)		- 56	ASTM D-97
Typical P	roperties of the Greas	e		
Color, Appearance			Black, Smooth	
Penetration 1/10 mm	Unworked		226	ASTM D-217
	Worked	60 X	230	
		10,000 X	275	
		100,000 X	-	
	NLGI Grade		3	
Density	gm/cc	25°C	1.06	ASTM D-1480
Dropping Point (°C)			None, Non-Melting	ASTM D-2265
Oil Separation	24 hours	100°C	0.2 %	FTM 791B, 321.2
Evaporation	24 hours	100°C	0.1 %	ASTM D-972
Water Washout	60 minutes	80°C	0.8 %	ASTM D-1264
Copper Corrosion	24 hours	100°C	None	ASTM D-4048
4 Ball Wear	60 min., 1200 RPM	75°C	0.57 mm	ASTM D-2266
	40 kg. load	150°C	-	
Low Temperature Starting Torque			-	
Torque (-40°C)	Running Torque	10 minutes	-	ASTM D-1478
gm-cm	Running Torque	60 minutes	-	
Oxidative Stability	168 hours	100°C	None	ASTM D-942
Approximate Volume Resistivity		ohm-cm	28	CTM-12
Bearing Rust Test				ASTM D-1743
Apparent Viscosity				

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product Material Safety Data Sheet for detailed safety information. (0409)

Nye Lubricants, Inc. 12 Howland Road, Fairhaven, MA 02719 USA Ph: 1.508.996.6721 Fx: 1.508.997.5285 nyelubricants.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we cannot guarantee the applicability of this information or the suitability of our products in any individual situation. For the same reason, the products discussed are sold without warranty, express or implied. Statements concerning the possible use of our products are not intended as recommendations to use our product in the infringement of any patent.