Rust Inhibited, PTFE Fortified

A medium viscosity, lithium soap, synthetic hydrocarbon grease fortified with PTFE to reduce friction. Intended for bearings, gears, slides, and mechanical applications requiring low friction.

Typical Value

-50 to 125

Lithium Soap Delvelahaelefia GM: 9986139

Test Method

Base Oil	Туре		Polyalphaolefin	
	Kinematic Viscosity	100°C	8.6 cSt	ASTM D-445
		40°C	51.7 cSt	ASTM D-445
	Viscosity Index		143	ASTM D-2270
	Flash Point	°C	278	ASTM D-92
	Pour Point	°C	-60	ASTM D-97
	Typical Properties of	the	Typical Value	Test Method
	Grease			
Color, Appearance			Off-white.	
Penetration	Unworked		267	ASTM D-217
(1/10 mm)	Worked	60 X	277	ASTM D-217
	NLGI Grade		2	ASTM D-217
Density		25°C	0.89 g/cm3	NYE CTM
Oil Separation	24 hour(s)	150°C	8.43 %	ASTM D-6184
Evaporation	24 hour(s)	150°C	1.24 %	ASTM D-972

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product MSDS for detailed safety information for this product. (1201)

Distributed By Newgate Simms Limited

Broughton Mills Road, Bretton, Chester, CH4 OBY, United Kingdom Ph: +44(0)1244 660771 Fx: +44(0)1244 661220 www.newgatesimms.co.uk info@newgatesimms.co.uk

Nye	Synthetic Lubricants		
	Innovative Solutions since 1844		

Recommended Service Range (°C)

Thickener

Lubricant Properties

RHEOLUBE 363F

广州孚润 400-992-6811