## **RHEOLUBE 380**



广州孚润 400-992-6811

## **EP Fortified, Rust Inhibited**

A lithium soap thickened, blended base oil gear grease suited for long life metal gears in automotive starters, power tools, and heavily loaded mechanical applications.

	Lubricant Properties		Typical value	Test Method
Recommended Service Range (°C)		-50 to 130		
Thickener	<b>- - - - - -</b>		Lithium Soap	
Base oil	Туре		PAO/Ester	
	Kinematic viscosity	100°C	6.228 cSt	ASTM D-445
		40°C	33.593 cSt	
		-40°C	14410 cSt	
	Viscosity Index		136.7	ASTM D-2270
	Flash point	C°	252	ASTM D-92
	Pouring point	°C	-52	ASTM D-97
	Typical Properties of	f the	Typical value	Test Method
	Grease			
Color, Appearance			Black, Smooth	
Penetration	Worked	60X	275	ASTM D-217
(1/10 mm)	Worked	10K	292	
	Unworked		261	
	NLGI Grade		2	
Density		25°C	0.91 g/cm <sup>3</sup>	NYE CTM
Oil Separation	24 hour(s)	100°C	4.5 %	ASTM D-6184
Evaporation	24 hour(s)	100°C	0.22 %	NYE CTM
		150°C	2.76 %	

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1511)

Distributed by Newgate Simms Limited

Broughton Mills Road, Bretton, Chester, CH4 0BY, United Kingdom +44(0)1244 660771 www.newgatesimms.com info@newgatesimms.com